

Application No.: 09/729,557
Response dated: August 19, 2004
Reply to Office Action of: May 20, 2004

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A process to polymerize one or more olefin(s) in the presence of a catalyst composition comprising combining a solid or a slurry comprising one or more ~~bulky ligand~~ metallocene catalyst compounds, a support and or one or more activator(s) with a solution comprising one or more phenoxide catalyst compounds, and thereafter, introducing the combination into a polymerization reactor, wherein at least 50% of said one or more metallocene catalyst compounds and at least 50% of said one or more phenoxide catalyst compounds are deposited in or on said support.
2. (Original) The process of claim 1 wherein the slurry comprises a supported alumoxane and or a supported modified alumoxane.
3. (Currently Amended) The process of claim 1 wherein the slurry is formed by combining a supported activator with a liquid and a ~~bulky ligand~~ metallocene catalyst compound.
4. (Currently Amended) The process of claim 1 wherein the slurry comprises a supported catalyst system comprising a ~~bulky ligand~~ metallocene catalyst compound, an activator and a support.
5. (Currently Amended) The process of claim 4 wherein the supported catalyst system is prepared by combining the ~~bulky ligand~~ metallocene catalyst

2000U044[1].US.111.8.19.04

- 2 -

Application No.: 09/729,557
Response dated: August 19, 2004
Reply to Office Action of: May 20, 2004

compound, the activator and the support in a solvent and thereafter removing the solvent.

6. (Original) The process of claim 4 wherein the supported catalyst system is prepared by combining the catalyst compound, the activator and the support in a solvent and thereafter spray drying the mixture.
7. (Original) The process of claim 1 wherein after combination at least 50% of the catalyst compounds are deposited in or on the support.
8. (Original) The process of claim 1 wherein after combination at least 80% of the catalyst compounds are deposited in or on the support.
9. (Original) The process of claim 1 wherein the activator comprises a non-coordinating anion or an ionizing compound.
10. (Original) The process of claim 1 wherein the activator comprises one or more from the group consisting of: trimethylammonium tetraphenylborate, triethylammonium tetraphenylborate, tripropylammonium tetraphenylborate, tri(n-butyl)ammonium tetraphenylborate, tri(t-butyl)ammonium tetraphenylborate, N,N-dimethylanilinium tetraphenylborate; N,N-diethylanilinium tetraphenylborate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate, trimethylammonium tetrakis(pentafluorophenyl)borate, triethylammonium tetrakis(pentafluorophenyl)borate, tripropylammonium tetrakis(pentafluorophenyl)borate, tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate, tri(sec-butyl)ammonium tetrakis(pentafluorophenyl) borate, N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate, N,N-diethylanilinium

Application No.: 09/729,557
 Response dated: August 19, 2004
 Reply to Office Action of: May 20, 2004

tetrakis(pentafluorophenyl) borate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate, trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate, tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate; tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate, dimethyl (t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate, N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl) borate, N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluoro-phenyl) borate, and N,N-dimethyl-(2,4,6-trimethylanilinium)tetrakis-(2,3,4,6-tetrafluorophenyl) borate, di-(i-propyl)ammonium tetrakis(pentafluorophenyl) borate, and dicyclohexylammonium tetrakis(pentafluorophenyl) borate, triphenylphosphonium tetrakis(pentafluorophenyl) borate, tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate.

11. (Currently Amended) The process of claim 1 wherein the ~~bulky ligand~~ metallocene catalyst compound is represented by the formula:



where M is a Group 3 to 12 metal or a lanthanide or actinide element, L^A , L^B and L^C are each independently bulky ligands selected from the group consisting of cyclopentadienyl ligands, cyclopentaphenanthrenyl ligands, indenyl ligands, benzindenyl ligands, fluorenyl ligands, octahydrofluorenyl ligands, cyclooctatetraendiyl ligands, cyclopentacyclododecene ligands, azenyl ligands, azulene ligands, pentalene ligands, phosphoyl ligands, phosphinimine, aminomethylphosphine ligands, pyrrolyl ligands, pyrozolyl

Application No.: 09/729,557
Response dated: August 19, 2004
Reply to Office Action of: May 20, 2004

ligands, carbazolyl ligands, borabenzene ligands, B-diketiminato ligands, fullerenes and hydrogenated versions thereof, each Q is independently a leaving group, A is a bridging group containing at least one Group 13 to 16 atom, J is a heteroatom ancillary ligand, and n is 0, 1 or 2, in formula III, M is bound to L^C and J, and A is bound to L^C and J.

12. (Currently Amended) The method of claim 1 wherein the bulky ligand metallocene catalyst compound is represented by the formula:




where M is a Group 3 to 16 metal,

L^D is a bulky ligand that is bonded to M selected from the group consisting of selected from the group consisting of cyclopentadienyl ligands, cyclopentaphenanthrenyl ligands, indenyl ligands, benzindenyl ligands, fluorenyl ligands, octahydrofluorenyl ligands, cyclooctatetraendiyl ligands, cyclopentacyclododecene ligands, azenyl ligands, azulene ligands, pentalene ligands, phosphoyl ligands, phosphinimine, aminomethylphosphine ligands, pyrrolyl ligands, pyrolyl ligands, carbazolyl ligands, borabenzene ligands, B-diketiminato ligands, fullerenes and hydrogenated versions thereof, each Q is independently bonded to M and Q₂(YZ) forms a uncharged polydentate ligand; A or Q is a univalent anionic ligand also bonded to M;

X is a univalent anionic group when n is 2 or X is a divalent anionic group when n is 1; n is 1 or 2.


Application No.: 09/729,557
 Response dated: August 19, 2004
 Reply to Office Action of: May 20, 2004

13. (Currently Amended) The method of claim 1 wherein the bulky ligand metallocene catalyst compound is represented by the formula:




where M is a metal selected from Group 3 to 13 or lanthanide and actinide series of the Periodic Table of Elements; Q is bonded to M and each Q is a monovalent, bivalent, or trivalent anion; X and Y are bonded to M; one or more of X and Y are heteroatoms; Y is contained in a heterocyclic ring J, where J comprises from 2 to 50 non-hydrogen atoms, Z is bonded to X, where Z comprises 1 to 50 non-hydrogen atoms; t is 0 or 1; when t is 1, A is a bridging group joined to at least one of X, Y or J, q is 1 or 2; n is an integer from 1 to 4.

14. (Original) The process of claim 1 wherein the phenoxide catalyst compound is represented by the formula:



or

Application No.: 09/729,557
 Response dated: August 19, 2004
 Reply to Office Action of: May 20, 2004



wherein

R^1 is hydrogen or a C_4 to C_{100} group and may or may not also be bound to M, and at least one of R^2 to R^5 is a group containing a heteroatom, the rest of R^2 to R^5 are independently hydrogen or a C_1 to C_{100} group, and any of R^2 to R^5 also may or may not be bound to M,

O is oxygen,

M is a group 3 to group 10 transition metal or lanthanide metal,

n is the valence state of the metal M,

Q is an alkyl, halogen, benzyl, amide, carboxylate, carbamate, thiolate, hydride or alkoxide group, or a bond to an R group containing a heteroatom which may be any of R^1 to R^5 .

15. (Original) The process of claim 1 wherein the polymerization reactor is a gas phase polymerization reactor.
16. (Original) The process of claim 1 wherein the polymerization reactor is a slurry phase polymerization reactor.
17. (Currently Amended) The process of claim 1 wherein the bulky ligand

Application No.: 09/729,557
Response dated: August 19, 2004
Reply to Office Action of: May 20, 2004

metallocene catalyst compound is selected from one of the group consisting of: bis(cyclopentadienyl)titanium dimethyl, bis(cyclopentadienyl)titanium diphenyl, bis(cyclopentadienyl)zirconium dimethyl, bis(cyclopentadienyl)zirconium diphenyl, bis(cyclopentadienyl) hafnium methyl and diphenyl, bis(cyclopentadienyl)titanium di-neopentyl, bis(cyclopentadienyl)zirconium di-neopentyl, bis(cyclopentadienyl)titanium dibenzyl, bis(cyclopentadienyl)zirconium dibenzyl, bis(cyclopentadienyl) vanadium dimethyl, bis(cyclopentadienyl)titanium methyl chloride, bis(cyclopentadienyl)titanium ethyl chloride, bis(cyclopentadienyl) titanium phenyl chloride, bis(cyclopentadienyl)zirconium methyl chloride, bis (cyclopentadienyl)zirconium ethyl chloride, bis(cyclopentadienyl)zirconium phenyl chloride, bis(cyclopentadienyl)titanium methyl bromide, cyclopentadienyl titanium trimethyl, cyclopentadienyl zirconium triphenyl, cyclopentadienyl zirconium trineopentyl, cyclopentadienyl zirconium trimethyl, cyclopentadienyl hafnium triphenyl, cyclopentadienyl hafnium trineopentyl, cyclopentadienyl hafnium trimethyl, pentamethylcyclopentadienyl titanium trichloride, pentaethylcyclopentadienyl titanium trichloride; bis(indenyl)titanium diphenyl or dichloride, bis(methylcyclopentadienyl)titanium diphenyl or dihalide, bis(1,2-dimethylcyclopentadienyl)titanium diphenyl or dichloride, bis(1,2-diethylcyclopentadienyl)titanium diphenyl or dichloride, bis(pentamethylcyclopentadienyl) titanium diphenyl or dichloride;

Application No.: 09/729,557
Response dated: August 19, 2004
Reply to Office Action of: May 20, 2004

dimethyl silyldicyclopentadienyl titanium diphenyl or dichloride,
methyl phosphine dicyclopentadienyl titanium diphenyl or dichloride,
methylenedicyclopentadienyl titanium diphenyl or dichloride,
isopropyl(cyclopentadienyl)(fluorenyl)zirconium dichloride,
isopropyl(cyclopentadienyl)(octahydrofluorenyl)zirconium dichloride,
diisopropylmethylene(cyclopentadienyl)(fluorenyl)zirconium
dichloride,
diisobutylmethylene(cyclopentadienyl)(fluorenyl) zirconium dichloride,
ditertbutylmethylene(cyclopentadienyl)(fluorenyl)zirconium dichloride,
cyclohexylidene(cyclopentadienyl)(fluorenyl)zirconium dichloride,
diisopropylmethylene(2,5-
dimethylcyclopentadienyl)(fluorenyl)zirconium dichloride,
isopropyl(cyclopentadienyl)(fluorenyl)hafnium dichloride,
diphenylmethylene(cyclopentadienyl)(fluorenyl)hafnium dichloride,
diisopropylmethylene(cyclopentadienyl)(fluorenyl)hafnium dichloride,
diisobutylmethylene(cyclopentadienyl)(fluorenyl)hafnium dichloride,
ditertbutylmethylene(cyclopentadienyl)(fluorenyl)hafnium dichloride,
cyclohexylidene(cyclopentadienyl)(fluorenyl)hafnium dichloride,
diisopropylmethylene(2,5-dimethylcyclopentadienyl) (fluorenyl)-
hafnium dichloride, isopropyl(cyclopentadienyl)(fluorenyl)titanium
dichloride,
diphenylmethylene(cyclopentadienyl)(fluorenyl)titanium dichloride,
diisopropylmethylene(cyclopentadienyl)(fluorenyl)titanium dichloride,
diisobutylmethylene(cyclopentadienyl)(fluorenyl)titanium dichloride,
ditertbutylmethylene(cyclopentadienyl)(fluorenyl)titanium dichloride,
cyclohexylidene(cyclopentadienyl)(fluorenyl)titanium dichloride,
diisopropylmethylene(2,5 dimethylcyclopentadienyl fluorenyl)titanium
dichloride, racemic-ethylene bis(1-indenyl)zirconium (W) dichloride,

Application No.: 09/729,557
Response dated: August 19, 2004
Reply to Office Action of: May 20, 2004

racemic-ethylene bis (4,5,6,7-tetrahydro-1-indenyl) zirconium (IV) dichloride,
racemic-dimethylsilyl bis (1-indenyl) zirconium (IV) dichloride,
racemic-dimethylsilyl bis (4,5,6,7-tetrahydro-1-indenyl) zirconium (IV) dichloride, racemic-1,1,2,2-tetramethylsilanylene bis (1-indenyl) zirconium (IV) dichloride, racemic-1,1,2,2-tetramethylsilanylene bis (4,5,6,7-tetrahydro-1-indenyl) zirconium (IV) dichloride, ethylidene (1-indenyl tetramethylcyclopentadienyl) zirconium (IV) dichloride,
racemic-dimethylsilyl bis (2-methyl-4-t-butyl-1-cyclopentadienyl) zirconium (IV) dichloride,
racemic-ethylene bis (1-indenyl) hafnium (IV) dichloride, racemic-ethylene bis (4,5,6,7-tetrahydro-1-indenyl) hafnium (IV) dichloride, racemic-dimethylsilyl bis (1-indenyl) hafnium (IV) dichloride, racemic-dimethylsilyl bis (4,5,6,7-tetrahydro-1-indenyl) hafnium (IV) dichloride, racemic-1,1,2,2-tetramethylsilanylene bis (1-indenyl) hafnium (IV) dichloride, racemic-1,1,2,2-tetramethylsilanylene bis (4,5,6,7-tetrahydro-1-indenyl) hafnium (IV) dichloride, ethylidene (1-indenyl-2,3,4,5-tetramethyl-1-cyclopentadienyl) hafnium (IV) dichloride,
racemic-ethylene bis (1-indenyl) titanium (IV) dichloride, racemic-ethylene bis (4,5,6,7-tetrahydro-1-indenyl) titanium (IV) dichloride, racemic-dimethylsilyl bis (1-indenyl) titanium (IV) dichloride, racemic-dimethylsilyl bis (4,5,6,7-tetrahydro-1-indenyl) titanium (IV) dichloride,
racemic-1,1,2,2-tetramethylsilanylene bis (1-indenyl) titanium (IV) dichloride
racemic-1,1,2,2-tetramethylsilanylene bis (4,5,6,7-tetrahydro-1-indenyl) titanium (IV) dichloride, and ethylidene (1-indenyl-2,3,4,5-tetramethyl-1-cyclopentadienyl) titanium (IV) dichloride.

Application No.: 09/729,557
Response dated: August 19, 2004
Reply to Office Action of: May 20, 2004

18. (Original) The process of claim 1 wherein the phenoxide catalyst compound is selected from one of the group consisting of:

(*N*-methyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-ethyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-*iso*-propyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-*t*-butyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-benzyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-hexyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-phenyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-methyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-benzyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dichloride;
bis(*N*-benzyl-3,5-di-*t*-butylsalicylimino)zirconium(IV) dipivalate;
bis(*N*-benzyl-3,5-di-*t*-butylsalicylimino)titanium(IV) dipivalate;
bis(*N*-benzyl-3,5-di-*t*-butylsalicylimino)zirconium(IV)
di(bis(dimethylamide));
bis(*N*-*iso*-propyl-3,5-di-*t*-amylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-*iso*-propyl-3,5-di-*t*-octylsalicylimino)zirconium(IV) dibenzyl;
bis(*N*-*iso*-propyl-3,5-di-(1',1'-dimethylbenzyl)salicylimino)zirconium(IV)
dibenzyl;
bis(*N*-*iso*-propyl-3,5-di-(1',1'-dimethylbenzyl)salicylimino)titanium(IV)
dibenzyl;
bis(*N*-*iso*-propyl-3,5-di-(1',1'-dimethylbenzyl)salicylimino)hafnium(IV)
dibenzyl;
bis(*N*-*iso*-butyl-3,5-di-(1',1'-dimethylbenzyl)salicylimino)zirconium(IV)
dibenzyl;
bis(*N*-*iso*-butyl-3,5-di-(1',1'-dimethylbenzyl)salicylimino)zirconium(IV)
dichloride;

Application No.: 09/729,557

Response dated: August 19, 2004

Reply to Office Action of: May 20, 2004

bis(*N*-hexyl-3,5-di-(1',1'-dimethylbenzyl)salicylimino)zirconium(IV)
 dibenzyl;
 bis(*N*-phenyl-3,5-di-(1',1'-dimethylbenzyl)salicylimino)zirconium(IV)
 dibenzyl;
 bis(*N*-*iso*-propyl-3,5-di-(1'-methylcyclohexyl)salicylimino)zirconium(IV)
 dibenzyl;
 bis(*N*-benzyl-3-*t*-butylsalicylimino)zirconium(IV) dibenzyl;
 bis(*N*-benzyl-3-triphenylmethylsalicylimino)zirconium(IV) dibenzyl;
 bis(*N*-*iso*-propyl-3,5-di-trimethylsilylsalicylimino)zirconium(IV) dibenzyl;
 bis(*N*-*iso*-propyl-3-(phenyl)salicylimino)zirconium(IV) dibenzyl;
 bis(*N*-benzyl-3-(2',6'-di-*iso*-propylphenyl)salicylimino)zirconium(IV)
 dibenzyl;
 bis(*N*-benzyl-3-(2',6'-di-phenylphenyl)salicylimino)zirconium(IV) dibenzyl;
 bis(*N*-benzyl-3-*t*-butyl-5-methoxysalicylimino)zirconium(IV) dibenzyl;
 bis(2-(2H-benzotriazol-2-yl)-4,6-di-*t*-amylphenoxide)zirconium(IV) dibenzyl;
 bis(2-(2H-benzotriazol-2-yl)-4,6-di-*t*-amylphenoxide)zirconium(IV)
 dichloride;
 bis(2-(2H-benzotriazol-2-yl)-4,6-di-*t*-amylphenoxide)zirconium(IV)
 di(bis(dimethylamide)); bis(2-(2H-benzotriazol-2-yl)-4,6-di-(1',1'-
 dimethylbenzyl)phenoxide)zirconium(IV) dibenzyl; bis(2-(2H-benzotriazol-2-
 yl)-4,6-di-*t*-amylphenoxide)titanium(IV) dibenzyl; bis(2-(2H-benzotriazol-2-
 yl)-4,6-di-(1',1'-dimethylbenzyl)phenoxide)titanium(IV) dibenzyl; bis(2-(2H-
 benzotriazol-2-yl)-4,6-di-(1',1'-dimethylbenzyl)phenoxide)titanium(IV)
 dichloride; bis(2-(2H-benzotriazol-2-yl)-4,6-di-(1',1'-
 dimethylbenzyl)phenoxide)hafnium(IV) dibenzyl; (*N*-phenyl-3,5-di-(1',1'-
 dimethylbenzyl)salicylimino)zirconium(IV) tribenzyl; (*N*-(2',6'-di-*iso*-
 propylphenyl)-3,5-di-(1',1'-dimethylbenzyl)salicylimino)zirconium(IV)
 tribenzyl; (*N*-(2',6'-di-*iso*-propylphenyl)-3,5-di-(1',1'-

Application No.: 09/729,557
 Response dated: August 19, 2004
 Reply to Office Action of: May 20, 2004

dimethylbenzyl)salicylimino)titanium(IV) tribenzyl; and (*N*-(2',6'-di-*iso*-propylphenyl)-3,5-di-(1',1'-dimethylbenzyl) salicylimino)zirconium(IV) trichloride.

19. (Currently Amended) The process of claim 1 wherein the ~~bulky ligand~~ metallocene catalyst compound comprises bis(2,4 methylbutylcyclopentadienyl) zirconium dihalide and the phenoxide catalyst compound comprises bis(*N*-iso-butyl-3-*t*-butylsalicylimino)zirconium (IV)dibenzyl.
20. (Original) The process of claim 1 wherein prior to combination the solution comprises less than 1 weight percent activator.
21. (Original) The method of claim 19 wherein the activator comprises supported alumoxane.
22. (Original) The method of claim 1 wherein the slurry comprises mineral oil and has a viscosity of about 130 to about 2000 cP at 20°C.
23. (Original) The method of claim 1 wherein the combination of the solution and the slurry has a viscosity of about 130 to about 2000 cP at 20°C.
24. (Original) The method of claim 1 wherein the solution does not comprise mineral oil and comprises up to 20 weight % of the combination of the solution and the slurry.

Application No.: 09/729,557
Response dated: August 19, 2004
Reply to Office Action of: May 20, 2004

25. (Original) The method of claim 1 wherein the solution comprises mineral oil and comprises up to 90 weight % of the combination of the solution and the slurry.
26. The method of claim 1 wherein the solution and the slurry are mixed for up to about 120 minutes prior to being introduced into the reactor.
27. (Original) The method of claim 1 wherein the solution and the slurry are mixed for about 1 minute to about 60 minutes prior to being introduced into the reactor.
28. - 36. (Withdrawn)